





Images do not accurately portray size or color.

Accu-Vu™ Imaging:



Comments:

General Report Comments:

American Gemological Laboratories
580 Fifth Avenue • New York, NY 10036 • 212.704.0727 • www.agl-gemlab.com

(Please see the back of this document for important disclaimer information) © 2026 AGL

M. Chaipaksa
Monrudee Chaipaksa, Senior Gemologist

Christopher P. Smith
Christopher P. Smith, President



Document No: 1153734 Validation Date: 29 January 2026

Identification

Mineral Type: Natural Corundum Transparency: Transparent

Variety: Pink Sapphire Color Description: Pink

Carat Weight: 6.63 cts Shape: Square Cushion

Measurements: 10.35 x 10.00 x 7.14 mm Cutting Style: Modified Mixed Cut

Comments: Color test: Stable color determined.

American Gemological Laboratories™
America's first and most highly respected origin lab.

Founded in 1977,
AGL is an internationally recognized gemstone
testing facility, specializing in comprehensive
colored stone analyses.

AGL has the distinction of being the
first laboratory in the United States to issue
Country-of-Origin reports. Our company and its
principals have a long tradition of research into the
detection of and reporting on gem identification-
and-classification, gemstone treatments and
provenance determinations.

Our staff is composed of experts in the field
of gemstone testing and reporting. Our findings
reflect the latest knowledge and analytical
techniques to ensure the highest standards
are applied on every stone we test.

AGL's testing and reporting
methodology provide you with unsurpassed quality
and reliability. We are committed to providing
the highest level of service and reporting
that our clients and the industry have
come to expect from the AGL.

Origin
Provenance: Madagascar

Comments: Based on available gemological information, it is the opinion of the
Laboratory that the origin of this material would be classified as
Madagascar.



Enhancement

Standard: Low temperature heating Additional: Clarity enhancement: None

Comments: Gemological evidence of relatively low temperature heating.
Pink sapphires are commonly heated to modify their color and appearance.

1	2	3	4	5	6	7	8	9	10	None	Insignificant	Minor	Moderate	Strong	Prominent
Excellent	Very Good	Good	Fair	Poor	Extremely Rare	Very Rare	Rare	Uncommon	Common	Very Common					

Enhancement Stability Index™

Degree of Clarity Enhancement & Relative Rarity™